



4500 SERIES SPARKLESCENT COLORS SET INSTRUCTIONS

Sets are designed to use Sparklescent Colors as a mid-coat over a color-keyed base for improved coverage and easier application. Color-keyed base allows Sparklescent Color to cover with less material required than over a white base. Small sets contain enough material to paint a motorcycle and a small car. Large sets contain enough material to paint an average to large-sized vehicle.

Mango (Set #s 4970, 4971), Tequila Yellow (4974, 4975), Rock Star Red (4980, 4981) Sets

1. Start with a tinted sealer made by mixing 4001 Sealer White with approximately 15% 4200 Series Semi-Opaque Color. Reduce mixture 10% with 4011 Flash Reducer. After curing, dry sand smooth using 600 – 800 grit paper to remove any surface roughness.
2. Apply the 4200 Series Semi-Opaque Colors as the base color over the tinted sealer. Reduce 10% with 4011 Flash Reducer. Allow colors to dry.
3. Apply Sparklescent Color as a mid-coat over color keyed base. Reduce 10% with 4011 Flash Reducer. Apply lightly, avoid wetted coats and building up material in excess.
4. After curing, top coat colors with a durable, clear. We recommend a catalyzed, 2-part urethane clear for an automotive finish.

Electric Green (Sets #s 4972, 4973), Toxic Green (4976, 4977) Porn Star Pink (4978, 4979), Real Teal (4982, 4983), Fine Wine (4986, 4987) sets

1. Start with a tinted sealer made by mixing 4001 Sealer White with approximately 2:1 with 4200 Series Transparent Color. Reduce mixture 10% with 4011 Flash Reducer. After curing, dry sand smooth using 600 – 800 grit paper to remove any surface roughness.
2. Apply Sparklescent Color as a mid-coat over color keyed base. Reduce 10% with 4011 Flash Reducer. Apply lightly, avoid wetted coats and building up material in excess.
3. After curing, top coat colors with a durable, clear. We recommend a catalyzed, 2-part urethane clear for an automotive finish.

Nightmare Blue (#s 4984, 4985) & Blizzard Blue (4990, 4991) Sets

1. Start with a 4000 Series reduced 10% with 4011 Flash Reducer. After curing, dry sand smooth using 600 – 800 grit paper to remove any surface roughness.
2. Apply the 4300 Series Colors as the base color. Reduce 10% with 4011 Flash Reducer. Allow colors to dry.
3. Apply Sparklescent Color as a mid-coat over color keyed base. Reduce 10% with 4011 Flash Reducer. Apply lightly, avoid wetted coats and building up material in excess.
4. After curing, top coat colors with a durable, clear. We recommend a catalyzed, 2-part urethane clear for an automotive finish.

Bada Bling Silver Set (#s 4988, 4989)

1. Mix 4001 & 4001 Sealer White & Dark to make a medium grey sealer base. Reduce grey sealer mix 10% with 4011 Flash Reducer.
2. Mix 4332 Metallic Silver 2:1 4590 Bada Bling Silver. Reducer silver mixture 10% 4011 Flash Reducer. Best applied in a cross-hatched pattern to achieve a random, well-spaced orientation.
3. After curing, top coat colors with a durable, clear. We recommend a catalyzed, 2-part urethane clear for an automotive finish.